

MAR 1953 31-46

FOR OFFICIAL USE ONLY
UNCLASSIFIEDCLASSIFICATION ~~RESTRICTED~~
~~SECURITY INFORMATION~~CENTRAL INTELLIGENCE AGENCY
INFORMATION FROM
FOREIGN DOCUMENTS OR RADIO BROADCASTS

REPORT NO.

CD NO.

25X1A

COUNTRY USSR

DATE OF
INFORMATION 1947SUBJECT Scientific - Metals, lithium,
lithium minerals

DATE DIST. 17 Mar 1953

HOW
PUBLISHED Pamphlet

NO. OF PAGES 3

WHERE
PUBLISHED Moscow/LeningradDATE
PUBLISHED 1947SUPPLEMENT TO
REPORT NO.

LANGUAGE Russian

ILLEGIB

THIS DOCUMENT CONTAINS INFORMATION AFFECTING THE NATIONAL DEFENSE
OF THE UNITED STATES. WITHIN THE MEANING OF TITLE 18, SECTIONS 793
AND 794, OF THE U.S. CODE, AS AMENDED. ITS TRANSMISSION OR REVE-
LATION OF ITS CONTENTS TO OR RECEIPT BY AN UNAUTHORIZED PERSON IS
PROHIBITED BY LAW. THE REPRODUCTION OF THIS FORM IS PROHIBITED.

THIS IS UNEVALUATED INFORMATION

SOURCE

Trebovaniya promyshlennosti k kachestvu mineral'nogo syr'ya,
Vypusk 41, litay, published by All-Union Scientific Research
Institute of Mineral Raw Materials.USSR LITHIUM RESOURCES

E. P. Libman

The presence of lithium in large or small amounts has been established in 140 minerals. However, the number of lithium minerals of industrial significance is limited to four: lepidolite, spodumene, zinnwaldite, and amblygonite.

Appreciable concentrations of lithium occur in three types of deposits.

The first type is characterized by granitic pegmatites and is represented in the USSR by the Zavitinskoye deposit in the eastern Transbaykal. The pegmatite veins, exploited for a period of over 10 years, are of considerable thickness and run for many hundreds of meters. Individual veins are traced in strike up to 1,500 meters. Lithium minerals are represented mainly by spodumene, and also by petalite and amblygonite.

Pegmatites of this deposit show definite signs of passing through pneumatogenic processes as revealed by the presence of greisens. The thickness of greisenized portions in certain veins varies from 0.4 to 20 meters. By a number of common features the Zavitinskoye deposit approaches in its genetic type the Etta deposit of the Black Hills region in South Dakota.

The second type of lithium deposit is represented by pneumatolytic veins of the tin-wolfram group, containing zinnwaldite. Deposits of this type are few and commercially insignificant. In Czechoslovakia, the tin-bearing veins of Zinnwald, rich in feldspar, contain a large amount of zinnwaldite with a low concentration of lithium, 1-1.2%. Similar deposits occur in Saxony.

25X1A

25X1A

The third type includes the waters of mineral springs and brines in which lithium is concentrated jointly with sodium, potassium, boron and other salts.

In the USSR, this type of lithium concentration has been detected in many places, for example, jointly with alkalies in numerous salt lakes of Western Siberia. Study of inland salt lakes of the Aral-Caspian depression reveals accumulation of lithium in these lakes. Mineral springs of the Caucasus, Transbaykal, and other areas also show the presence of lithium.

There are no generally established standards for lithium ores or concentrates. Therefore, evaluation of the quality of these ores is usually done on the basis of industrial experience, small for the time being, gained by mining deposits already in exploitation.

Spodumene and zinnwaldite are found sometimes in the form of large crystals whose size permits obtaining commercial concentrates by hand picking. Their content in rocks is greatly varied even within a single deposit.

More frequently, lithium minerals are characterized by small size, and their extraction from ores requires mechanical concentration. Technical literature gives no adequate data on the lithium content in such ores but, obviously, it is also quite divergent in this case.

Scarcity of natural economically sound concentrations of lithium minerals requires of geologists the most accurate registration of each finding of such minerals. This is especially important in the light of the fact that a variation of their content in rocks may give unexpectedly favorable results during subsequent prospecting.

Prior to the revolution, all requirements for lithium products in Russia were covered exclusively by import, mainly from Germany. At present, a number of lithium deposits in the USSR, mainly in the form of spodumene and lepidolite, are being studied in detail. Domestic production of lithium preparation and compounds entirely satisfies demands of the national economy for these products.

The following table presents the chemical composition of lithium minerals from such deposits of the USSR.

ILLEGIB

Name of Mineral and Deposit	SiO 2	Al O 2 3	K O 2	Rb O 2	Cs O 2	Li O 2	Na O 2	CaF 2	Fe O 2 3	MnO	CaO	MgO	H O 2
Lepidolite													
Lipovskoye	50.35	26.30	9.04	--	--	5.49	--	5.20	--	1.23	--	--	--
Gora Veron- chikha	50.30	25.25	9.84	--	2.04	5.31	1.91	5.22	0.05	--	0.25	0.20	0.71
Yuzhakovo (Ural)	50.96	22.20	11.39	--	--	5.05	0.54	8.71	--	5.38	--	--	--
Savateyevskoye (from tailings heap)	51.50	24.35	6.31	0.40	0.29	1.29	2.21	--	0.70	4.36	0.12	4.36	--
Spodumene													
Zavitinskoye	53.53	27.88	0.29	--	--	0.92	0.95	--	0.28	0.11	0.21	0.02	0.06

25X1A